

Application No. 10/014,452

**AMENDMENT TO THE CLAIMS**

Please replace the currently pending claims with the following amended claims:

1. (Currently Amended) An endless seamed flexible belt comprising a first end and a second end, each of the first end and the second end comprising a plurality of mutually mating elements which join in an interlocking relationship to form a seam, the belt comprising a polyimide substrate and the seam comprising an adhesive comprising a polyamide polymer, oxalic acid, an electrically conductive filler, and a plasticizer selected from the group consisting of alcohols, amines, thiols, organic acids, oligomers, and mixtures thereof, wherein said plasticizer is present in the adhesive in an amount of from about 0.1 to about 80 percent by weight of total solids.

2. (Cancelled)

3. (Cancelled)

4. (Previously Presented) An endless seamed flexible belt in accordance with claim 1, wherein said plasticizer is selected from the group consisting of bisphenols, paratoluene sulfonamides, phosphates, esters, castor oil, and mixtures thereof.

5. (Cancelled)

6. (Original) An endless seamed flexible belt in accordance with claim 1, wherein said plasticizer is present in the adhesive in an amount of from about 1 to about 50 percent by weight of total solids.


7. (Cancelled)

8. (Currently Amended) An endless seamed flexible belt in accordance with claim ~~[[7]]~~ 1, wherein said polyamide comprises pendant groups selected from the group consisting of methoxy, ethoxy and hydroxy pendant groups.

Application No. 10/014,452

9. (Original) An endless seamed flexible belt in accordance with claim 8, wherein said pendant groups are methylene methoxy pendant groups.

10. (Original) An endless seamed flexible belt in accordance with claim 1, wherein said polyamide has the following general formula:



wherein R is selected from the group consisting of hydrogen, alkyl having from about 1 to about 20 carbons, alkoxy having from about 1 to about 20 carbons, alkyl alkoxy having from about 1 to about 20 carbons, and alkylene alkoxy having from about 1 to about 20 carbons, and wherein n is a number of from about 50 to about 1,000.

11. (Original) An endless seamed flexible belt in accordance with claim 10, wherein R is a methylene methoxy group.

12. (Cancelled)

13. (Currently Amended) An endless seamed flexible belt in accordance with claim [[12]] 1, wherein said electrically conductive filler is a quaternary ammonium salt.

14. (Currently Amended) An endless seamed flexible belt in accordance with claim [[12]] 1, wherein said electrically conductive filler is selected from the group consisting of carbon fillers, metal oxide fillers, polymer fillers, charge transporting molecules, and mixtures thereof.

15. (Original) An endless seamed flexible belt in accordance with claim 14, wherein said electrically conductive filler is a carbon filler selected from the group consisting of carbon black, graphite, fluorinated carbon, and mixtures thereof.

Application No. 10/014,452

16. (Original) An endless seamed flexible belt in accordance with claim 14, wherein said electrically conductive filler is a metal oxide filler selected from the group consisting of titanium dioxide, tin oxide, indium tin oxide, iron oxide, aluminum oxide, and mixtures thereof.

17. (Original) An endless seamed flexible belt in accordance with claim 14, wherein said electrically conductive filler is a polymer filler selected from the group consisting of polypyrrole, polyacrylonitrile, polythiophene, polyaniline and mixtures thereof.

18. (Original) An endless seamed flexible belt in accordance with claim 1, wherein said adhesive is crosslinked.

19. (Cancelled)

20. (Cancelled)

21. (Original) An endless seamed flexible belt in accordance with claim 1, wherein said belt is an intermediate transfer belt.

22. (Original) An endless seamed flexible belt in accordance with claim 1, wherein said plurality of mutually mating elements are in the form of a puzzle cut pattern.

23. (Original) An endless seamed flexible belt in accordance with claim 22, wherein said mutually mating elements comprise a first projection and a second receptacle geometrically oriented so that said second receptacle on the first end receives the first projection on the second end and wherein said first projection on said first end is received by said second receptacle on the second end to form a joint between the first and second ends.

Application No. 10/014,452

24. (Original) An endless seamed flexible belt comprising a first end and a second end, each of the first end and the second end comprising a plurality of mutually mating elements which join in an interlocking relationship to form a seam, said belt comprising a polyimide substrate, and the seam comprising an adhesive comprising a polyamide and a plasticizer selected from the group consisting of alcohol plasticizers, amine plasticizers, thiol plasticizers, organic acid plasticizers, and oligomer plasticizers.

25. (Previously Presented) An image forming apparatus for forming images on a recording medium comprising: a charge-retentive surface to receive an electrostatic latent image thereon; a development component to apply toner to the charge-retentive surface to develop the electrostatic latent image to form a developed image on said charge retentive surface; a transfer belt to transfer the developed image from the charge retentive surface to a copy substrate, wherein the transfer belt is an endless seamed flexible belt comprising a first end and a second end, each of the first end and the second end comprising a plurality of mutually mating elements which join in an interlocking relationship to form a seam, the transfer belt comprising a polyimide substrate and the seam comprising an adhesive comprising a polymer, oxalic acid and a plasticizer selected from the group consisting of alcohols, amines, thiols, organic acids, oligomers, and mixtures thereof, wherein said plasticizer is present in the adhesive in an amount of from about 0.1 to about 80 percent by weight of total solids and a fixing component to fuse the developed image to the copy substrate.

26. (Cancelled)